



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
E-mail: info@valpaint.it
C.F./P.IVA/R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it

SC 00067

BRILLANTE POLIURETANICO TRASPARENTE SX 300

Technical Sheet

NAME:

TYPE:

USE:

TECHNICAL DATA:

BRILLANTE POLIURETANICO SX 300

bright polyurethane

to use on wood, tables, level and vertical surfaces, painted with Granitone

specific weight: 1.000 ± 30 gr/LT. at 25°C

viscosity: 50" Ford 4 Part A

15" Ford 4 part A + B

yield: 6-7 m²/LT.

aspect: brilliance 95 gloss

colours: = = =

packaging: can of LT. 1 – LT. 5

on the surface: dust dry after 50 minutes at 20 °C. Dries in 120 minutes at 20°C

over painting: = = =

below the surface: 48 hours at 20°C

CHARACTERISTICS AND

RESISTANCE:

PREPARATION OF THE

SURFACE:

PREPARATION OF THE

PRODUCT:

bright polyurethane suitable for any kind of surfaces for interiors particularly painted with Granitone

prepare adequately the surface with Fondo Poliuretano N 133, sand it carefully and eliminate any dust left.

thinning: Brillante Poliuretano SX 300 must be catalysed with Catalizzatore 007 and brought at normal viscosity with Diluente MB

catalization relation: Brillante Poliu. SX 300 100 parts

Catalizzatore 007 100 parts

Diluente MB 10 - 20 parts

pot life: 90 minutes

system: spray gun

coats: min. 1 max. 2

interval between coats: not inferior to 40 minutes and not over 120 minutes

STABILITY:

component A (Brillante poliuretano SX 300) 1 year

component B (Catalizzatore 007) 6 months in closed/sealed cans

NOTE:

Wash the tools immediately after use with Diluente Poliuretano

Technical Sheet n° SC 00067 issued by the Control Quality Technician:

Edition n° 2

May 2001