



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
E-mail: info@valpaint.it
C.F./P.IVA/R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it

SC 00152

PRIMART 600 (water-based)

Technical sheet

NAME:

TYPE:

USE:

PRIMART 600

transpiring water-based primer for interiors and exteriors
professional white water-base paint characterised by a high.-covering and
whiteness It is a special primer created to get ancient effects typical of
ARTECO' 7.

TECHNICAL DATA:

specific weight: 1.515 ± 30 gr/LT. at 25°C
viscosity: = = =
yield : 10 - 12 m²/LT.
aesthetic effect: mat
colours: white (it is possible to colour the paint using
COLORI' or colours for water-base systems
resistant to UV rays)

DRYING TIME:

packaging: LT. 1 - LT. 2,5 - LT. 5
on the surface: 30 minutes at 20°C
overpainting: 2 hours at 20°C
below the surface: 12 hours at 20°C

**CHARACTERISTICS AND
RESISTENCE:**

It well resists to rural and marine atmosphere.
It does not prevent wall transpiration.

**PREPARATION OF THE
SUPPORT:**

Take away the old paints not properly stuck on the surface where
necessary with VALSTUC. Once the stucco gets well dried, apply a coat
of PRIMART 600 diluted with water at 50%, as fixative, if surfaces are
crumbling.

**PREPARATION OF THE
PRODUCT:**

dilution: 15 - 20% with drinkable water on the basis
of the weight

APPLICATION:

catalization relation: = = =
pot life: = = =
system: brush - roller - spray gun
coats: 1 - 2

NOTES:

- Drums and working tools must be immediately washed after use with water.
- Application temperature should not be inferior to +5°C. Do not apply on surfaces exposed directly to the sun and to the wind in order to prevent paint stripping off.

Technical Sheet n° SC 00152 issued by the Control Quality Department

Edition n° 4 October 2008