



VALPAINT S.p.A.  
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY  
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384  
E-mail: info@valpaint.it  
C.F./P.IVA/R.I. di AN 01108220425  
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it

SC 00056

## RITARDANTE Z 10

### TECHNICAL SHEET

**NAME:**

**TYPE:**

**USE:**

**TECHNICAL DATA:**

**RITARDANTE Z 10**

inorganic reagent

prolongation of the ZOT 78 pot life

**specific weight:** 890 gr/lit

**viscosity:** = = =

**yield:** = = =

**aspect:** = = =

**colours:** pale yellow

**packaging:** cans of 0,250 lt.

**on the surface:** = = =

**over painting:** = = =

**below the surface:** = = =

**DRYING TIME:**

**CHARACTERISTICS AND**

**RESISTANCE:**

it's a mixture inorganic reagent, able to prolong the ZOT 78 pot life. The catalysis time of ZOT 78 at 20 °C is about 10 minutes. Adding Ritardante Z 10 (50 gr per 100 Kg of ZOT 78) will obtain a delay of catalysis of about 30 minutes at 20°C. Adding Ritardante Z 10 (180 gr per 100 Kg. of ZOT 78) will obtain a catalysis delay until about 6 hours at 20°C. The catalysis time increase with drop in temperature and adding the Ritardante. Otherwise with temperature higher then 20 °C, the catalysis time become shorter proportionally to the increase of the temperature.

= = =

**PREPARATION OF THE**

**SURFACE:**

**PREPARATION OF THE**

**PRODUCT:**

**thinning:** = = =

**catalization relation:** = = =

**pot life:** = = =

**sistem:** = = =

**coats:** = = =

**APPLICATION:**

**NOTE:**

We advise to close carefully the cans after using.

Technical Sheet n° SC 00056 issued by the Control Quality Dpt.

Edition n° 1

January 1998